

Description

It is available in a large variety of decors and textures.

The melamine faced chipboard is used for furniture productions and inside walls.

The raw support has the mechanical and emission characteristics as indicated in the relative technical sheets.

Dimensions

Thickness: from 8 a 50 mm **Width:** 186 - 207 - 220 cm **Length:** 280 - 425 - 560 cm

Maximum size for melamine faced chipboard: max length 580 cm

For any special size request please contact our sales office.

Density

Type of panel	Methodological standards	Unit of measure	8-10 mm	>10-13 mm	>13-20 mm	>20-25 mm	>25-30 mm	>30-50 mm
Melamine faced	EN 323	Kg/mc	710 +/- 5%	700 +/- 5%	660 +/- 5%	650 +/- 5%	640 +/- 5%	630 +/- 5%

Surface Characteristics

Technical characteristics	Methodological standards	Figures	
		Unicolours	Wood
Abrasion Taber *	EN 14323:2017 par. 5.9	Class 3	Class 1
Tendency to retain dirt	UNI 9300:2015	Valutation 4	Valutation 4
Light fastness	UNI EN 15187:2007	Valutation 4	Valutation 5
Resistance to scratching*	EN 14323:2017 par. 5.5	1.5 N	3.5 N
Cold test check	UNI 9429:2015	Level 0	Level 0
Resistance to cold liquids	UNI EN 12720:2013	Class C	Class A
Resistance to wet heat	UNI EN 12721:2013	Class D	Class A
Resistance to dry heat	UNI EN 12722:2013	Class A	Class A

* The values observed can change according to the used decorative and finishing

