

## Description

The use of melamine kraft allows to improve the surface of the panels giving more uniformity of aspect and increasing wear resistance. It's available in **E1, CARB P2** or **F4 STARS** formaldehyde class. **FSC** mixed certification available.

The panel is available in **P2** and **P3 class**.

The raw support has the mechanical and emission characteristics as indicated in the relative technical sheets.

## Dimensions

**Thickness:** from 8 to 50 mm    **Width:** 186 - 207 - 220 cm    **Length:** 280 - 425 - 560 cm

For any special size request please contact our sales office.

### Density

Type of panel	Methodological standards	Unit of measure	>15-20 mm	>20-25 mm	>25-28 mm
Melamine faced	EN 323	Kg/m <sup>3</sup>	690 +/- 5%	670 +/- 5%	660 +/- 5%

### Surface Characteristics

Technical characteristics	Methodological standards	Figures	
		Unicolours	Wood
Abrasion Taber *	EN 14323:2017 par. 5.9	Class 3	Class 1
Tendency to retain dirt	UNI 9300:2015	Valutation 4	Valutation 4
Light fastness	UNI EN 15187:2007	Valutation 4	Valutation 5
Resistance to scratching*	EN 14323:2017 par. 5.5	1.5 N	3.5 N
Cold test check	UNI 9429:2015	Level 0	Level 0
Resistance to cold liquids	UNI EN 12720:2013	Class C	Class A
Resistance to wet heat	UNI EN 12721:2013	Class D	Class A
Resistance to dry heat	UNI EN 12722:2013	Class A	Class A

\* The values observed can change according to the used decorative and finishing

