

## / TECHNICAL SHEET

It is available in a large variety of decors and textures.

The melamine faced chipboard is used for furniture productions and inside walls.

The raw support is available in formaldehyde class E1, CARB P2, EPA TSCA and F4 STARS, with condition of use in class P2 and P3.

P2 panel is available in reaction to the fire class 3, thickness from 10 to 38 mm and also in reaction to the fire class B s1.

P3 panel is available only in reaction to the fire class 3.

100% recycled product, certified FSC® Mix

Dimensions / WIDTH 186 - 207 - 220 cm / THICKNESS da 8 a 50 mm

Density								
TYPE OF PANEL	METHODOLOGICAL STANDARDS	UNIT OF MEASURE	> 15-20 mm	> 20-25 mm	> 25-28 mm	> 28-32 mm	> 32-40 mm	> 40 mm
Melamine faced	EN 323	Kg/m <sup>3</sup>	710 +/- 5%	700 +/- 5%	660 +/- 5%	650 +/- 5%	640 +/- 5%	630 +/- 5%

Surface characteristics					
TECHNICAL CHARACTERISTICS		METHODOLOGICAL STANDARDS		FIGURES	
				UNICOLORS	PRINTED
Abrasion Taber*		EN 14323:2017 par. 5.9		Class 3	Class 1
Light fastness		UNI EN 15187:2007		Valutation 4	Valutation 5
Resistance to scratching*		EN 14323:2017 par. 5.5		≥ 1.5 N	≥ 1.5 N
Cold test check		UNI 9429:2015		Level 0	Level 0
Resistance to cold liquids		UNI EN 12720:2013		Class C	Class A
Resistance to wet heat		UNI EN 12721:2013		Class D	Class A
Resistance to dry heat		UNI EN 12722:2013		Class A	Class A

\* The values observed can change according to the used decorative and finishing.

Certified Management System



Certificazioni di sostenibilità

